



Betanox C

STAINLESS STEEL (Heat Resisting)

Stainless steel Electrode for high temperature oxidation resistance

CLASSIFICATION :	EN 1600	AWS A/SFA 5.4	IS 5206
	E 25 20 R 12	E 310-16	E 25.20 R26X

KEY FEATURES :

- Rutile coated electrode
- 25/20 type SS deposit
- Excellent resistance to cracking and fissuring
- Provides excellent stability and oxidation resistance upto 1150°C
- Excellent arc stability
- Low spatter loss
- Easy slag removal
- Suitable for all position
- Radiographic quality weld deposit

WELDING POSITION :



AC (70 OCV) / DCEP

TYPICAL APPLICATIONS :

- Joining difficult to weld steels such as armor plates and ferritic stainless steels as well as dissimilar steels
- Furnace parts, Annealing boxes, Carburizing pots, Gas turbine combustion chamber parts, hydrogenation and polymerization plant
- Welding of AISI 310 and similar steel
- Cladding side of stainless steels and dissimilar steels
- Suitable for materials 1.4710, 1.4713, 1.4745, 1.4762, 1.4823, 1.4832, 1.4837, 1.4840, 1.4841, 1.4845, 1.4846, 1.4848, 1.4849

REDRYING CONDITION : 300°C for 1 hr. (Also available in vacuum packed condition)

CHEMICAL COMPOSITION OF UNDILUTED WELD METAL, Wt % :

	C	Mn	Si	Cr	Ni	S	P
Typical	0.1	1.5	0.5	27.0	21.0	0.02	0.02
Specification	0.08-0.12	1.0-2.5	0.3-0.7	25.0-28.0	20.0-22.5	0.03 max	0.03 max

MECHANICAL PROPERTIES OF ALL WELD METAL :

	Condition	UTS, MPa	EL%
Typical	As Welded	600	37
Specification		560-660	30 min.

PARAMETERS - PACKING DATA :

Ø x L, mm	Amperage, A	Wt./Carton, Kg	Cartons/Box	Net wt./Box, Kg
2.5 x 300	50-75	2	5	10
3.15 x 300	80-100	2	5	10
4.0 x 300	110-140	2	5	10
5.0 x 300	150-180	2	5	10