



# Cromoten C

LOW ALLOY STEEL (High Temperature)

Basic Coated Electrode for welding 2.25 Cr-1Mo type creep resistant steel.

CLASSIFICATION :	EN 1599	AWS A/SFA 5.5	APPROVALS :
	E CrMo2 B 32 H5	E 9018-B3	ABS/IBR/NPCIL

### KEY FEATURES :

- Basic coated
- Low alloy steel Cr-Mo deposit
- Resistant to creep and heat upto 600°C
- Ductile and crack resistant and heat treatable weld
- Radiography quality weld metal

WELDING POSITION :		AC (70 OCV)/DCEP
--------------------	--	------------------

### TYPICAL APPLICATIONS :

- Welding of 2.25Cr-0.5Mo and 2.25Cr-1Mo type creep resistant steels
- Cr-Mo and Cr-Mo-V bearing steels for high temperature applications
- Main steam pipes of boilers in electric power plant, Boiler super heaters
- Joining of P5A materials
- Suitable for 12CrMo9-10, 10CrSiMoV7 German steels
- Joining ASTM A 335 Gr.P22, A 387 Gr.22 materials
- Application in refineries, power plants, pressure vessels, boilers

### CHEMICAL COMPOSITION OF UNDILUTED WELD METAL, Wt % :

	C	Mn	Si	Cr	Mo	S	P
Typical	0.08	0.6	0.4	2.4	1.0	0.02	0.02
Specification	0.05-0.09	0.45-0.75	0.20-0.65	2.0-2.5	0.9-1.2	0.03 max	0.03 max

### MECHANICAL PROPERTIES OF ALL WELD METAL :

	Condition	UTS, MPa	YS at 0.2% offset, MPa	EL%
Typical	PWHT: 690°C	660	580	22
Specification	for 1 Hr	625-740	540-640	20-24

Hardness, 3 Layer: 180-200 BHN

Diffusible H2 Content: <5 ml/100 gm

### SPECIAL TESTS : Creep Rupture Test at 600°C (100 MPa stress for min. 1000 hrs)

### PARAMETERS - PACKING DATA :

Ø x L, mm	Amperage, A	Approx. Pcs/Carton	Carton/Box	Approx. wt. of 1000 pcs, Kg.
2.5 x 350	60-90	230	4	22
3.15 x 450	100-140	112	4	44
4.0 x 450	140-180	75	4	66
5.0 x 450	190-250	54	4	91